

# Hempadur 47182

## Product characteristics

### Description

Hempadur 47182 is an anti-corrosive, modified polyamide adduct cured epoxy.

### Recommended use

Hempadur 47182 is recommended for atmospheric and immersion service used as a tie-coat between epoxy and physically drying coatings. For immersion service it can replace one anti-corrosive primer coat for the underwater coating system and at the same time act as tie-coat for antifouling. It may also be used as a "sealer" for existing antifouling.

### Service temperature:

- Maximum, dry exposure only: 80°C [176°F].

### Features

- High compatibility with old antifouling.
- Good corrosion resistance.
- Flexible application window.

## Product safety

**Flash point** 28°C [82°F]

### VOC content mixed product

Legislation	Value
EU	364 g/L [3.04 lb/US gal]
US (coatings)	364 g/L [3.04 lb/US gal]
US (regulatory)	364 g/L [3.04 lb/US gal]
China	364 g/L [3.04 lb/US gal]

According to specific legislation, see details in the Explanatory Notes available at Hempel website, [hempel.com](http://hempel.com) or at your local Hempel website.

### Handling

Handle with care. Before and during use, observe safety labels on packaging and paint containers and follow all local and national safety regulations. Always consult Hempel's Safety Data Sheet for this product along with the Product Data Sheet.

For professional use only.

## Product data

### Product code

47182

### Product components

Base 47188  
Curing agent 98470

### Standard shade\* / code

Light khaki brown 25150

### Gloss

Flat

### Volume solids

62 ± 2%

### Specific gravity

1.4 kg/L [12 lb/US gal]

### Reference dry film thickness

125 micron [4.9 mils]

## Surface preparation

### Cleanliness

- According to Hempel's Specification.

### New build:

- According to Hempel's Specification.

### Maintenance and Repair

- According to Hempel's Specification.

Consult Hempel's separate Surface Preparation Guidelines for more details.

# Hempadur 47182

## Application

### Mixing ratio

Base 47188 : Curing agent 98470  
(7 : 1 by volume)

Stir well before use.

### Thinner

Hempel's Thinner 08450

### Cleaner

Hempel's Tool Cleaner 99610

### Pot life

Product temperature	15°C [59°F]	20°C [68°F]	25°C [77°F]
Pot life	3 hours	2 hours	1½ hours

### Application method

Tool	Thinning max vol.	Application parameters
Airless spray	5%	Nozzle pressure: 230 bar [3300 psi] Nozzle orifice: 0.023"
Brush	5%	Not Applicable.

If brush or roller application is used, more coats will be necessary to achieve the specified dry film thickness. Spray data are indicative and subject to adjustment. Pressure is for a material temperature of 20°C [68°F].

### Film thickness

Specification range	Low	High	Recommended
Dry film thickness	75 micron [3.0 mils]	150 micron [5.9 mils]	125 micron [4.9 mils]
Wet film thickness	120 micron [5 mils]	250 micron [10 mils]	200 micron [8 mils]
Theoretical spreading rate	8.3 m <sup>2</sup> /L [340 sq ft/US gal]	4.1 m <sup>2</sup> /L [170 sq ft/US gal]	5 m <sup>2</sup> /L [200 sq ft/US gal]

Product may be specified in another film thickness than indicated depending on purpose and area of use. This will alter spreading rate, drying and curing time and overcoating interval. For best performance, avoid excessive film thickness.

### Application conditions

- Optimal paint temperature for proper mixing, pumping and spraying is: 20-25°C [68-77°F].
- To avoid condensation, apply on a clean and dry surface with a temperature that is at least 3°C [5°F] above the dew point.
- Surface temperature must be above -5°C [23°F] during application and curing.

### Application remarks

- If used as a sealer on old antifouling, any possible leached layer, patina or old layers with weak intercoat adhesion must be removed prior to application.

## Drying and overcoating

### Product compatibility

- Previous coat: According to Hempel's Specification. Recommended product is: Hempadur.
- Subsequent coat: According to Hempel's Specification.

### Drying time

Surface temperature		-5°C [23°F]	0°C [32°F]	20°C [68°F]	40°C [104°F]
Touch dry	hours	4	2	1	½
Surface dry	hours	22	16	5	2
Hard dry	hours	50	32	7	4

Determined for dry film thickness 125 micron [4.9 mils] at standard conditions, see Hempel's Explanatory Notes for details.

# Hempadur 47182

## Overcoating

Hempel's specification supersedes any guidelines indicated in the overcoating table

Quality name		0°C [32°F]	10°C [50°F]	20°C [68°F]
Atmospheric medium				
Hempatex Enamel 56360	Min	41 h	18 h	9 h
	Max	31 d	14 d	7 d
Immersion				
Hempel's Antifouling Globic 9000 78900	Min	41 h	18 h	9 h
	Max	22 d	10 d	5 d

Overcoating times are indicative for products of the same generic chemistry. Consult Hempel's specification for more information.

## Drying conditions

- To obtain the drying time stated, it is important to maintain sufficient ventilation during application, drying and curing.

## Overcoating details

- If the maximum overcoating interval is exceeded, roughening of the surface is necessary to ensure intercoat adhesion.
- The surface must be dry and clean prior to application.

## Other remarks

- Epoxy coats have an inherent tendency of chalking in outdoor exposure. This does not affect the performance of the coating.
- Hempel's Specification supersedes any recommendations given in the Product Data Sheets.

## Storage

### Shelf life

Ambient temperature	25°C [77°F]	35°C [95°F]
Base	36 months	24 months
Curing agent	24 months	16 months

Shelf life from date of production, when stored in original, unopened containers. Thereafter, the product quality must be re-inspected. Always check the best before date or expiry date on the label.

### Storage conditions

- Product must be stored according to local legislation, at maximum 40°C [104°F], without direct sunlight and protected from rain and snow.

## Additional documents

Additional information is available at the Hempel website [hempel.com](http://hempel.com) or at your local Hempel website:

- Explanatory Notes explaining the fields in this Product Data Sheet.
- Surface Preparation Guidelines.
- Application Guidelines for different application methods.
- General Application Guidelines

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. Accordingly, the buyer/applicator should have regard to the PDS supplied together with the relevant batch of the Product (and not an earlier version). In addition to the PDS, the buyer/applicator may receive some or all of the following specifications, statements and/or guidelines as listed below or as are available from the Hempel website under 'Products' at [www.hempel.com](http://www.hempel.com) (the "Additional documents"):

No.	Document description	Location/comments
1.	Technical Statement	One-off specific advice provided on request for specific projects
2.	Specification	Only issued for specific projects
3.	PDS	This document
4.	Explanatory Notes to the PDS	Available at <a href="http://www.hempel.com">www.hempel.com</a> and contain relevant information about the Product testing parameters
5.	Application Instruction	Where available, at <a href="http://www.hempel.com">www.hempel.com</a>
6.	Generic technical guidelines (e.g. on application and surface preparation)	Where available, at <a href="http://www.hempel.com">www.hempel.com</a>

In the event of a conflict of information between the PDS and the Additional documents, the order of priority of information shall be in the order as set out above. In such event you should also contact your representative at Hempel for clarification. Furthermore, the buyer/applicator must have full regard to the relevant Safety Data Sheet provided with each Product and which can also be downloaded from [www.hempel.com](http://www.hempel.com).

Hempel shall not be liable for defects where the application of the Product has not been made fully in accordance with the recommendations and requirements set out in the relevant PDS and the Additional Documents. The information and terms of this disclaimer apply to this PDS, the Additional documents and any other documents supplied by Hempel in respect of the Product. In addition, the Product is supplied and all technical assistance is given subject to Hempel's General Conditions of Sale, Delivery and Service, unless otherwise expressly agreed in writing.