

# Hempadur Multi-Strength 45703

## Product characteristics

### Description

Hempadur Multi-Strength 45703 is a self-priming, two-component, highbuild, aluminium pigmented pure epoxy paint which cures to an abrasion and corrosion resistant coating.

### Recommended use

As a primer for MULTI-STRENGTH systems for immersion and splash-zone service.

### Service temperature:

- Maximum, dry exposure only: 140°C [284°F].
- Maximum, in water (no temperature gradient): 50°C [122°F].
- Other liquids: Please contact Hempel.

## Product safety

**Flash point** 27°C [81°F]

### VOC content mixed product

Legislation	Value
EU	254 g/L [2.12 lb/US gal]
US (coatings)	254 g/L [2.12 lb/US gal]
US (regulatory)	254 g/L [2.12 lb/US gal]
China	254 g/L [2.12 lb/US gal]

According to specific legislation, see details in the Explanatory Notes available at Hempel website, [hempel.com](http://hempel.com) or at your local Hempel website.

### Handling

Handle with care. Before and during use, observe safety labels on packaging and paint containers and follow all local and national safety regulations. Always consult Hempel's Safety Data Sheet for this product along with the Product Data Sheet.

For professional use only.

## Product data

### Product code

45703

### Product components

Base 45705  
Curing agent 98750

### Standard shade / code

Aluminium red 19880 \*

### Gloss

Semi-gloss

### Volume solids

70 ± 2%

### Specific gravity

1.5 kg/L [13 lb/US gal]

### Reference dry film thickness

200 micron [7.9 mils]

## Surface preparation

### Cleanliness

- Remove oil, grease and other contaminants by suitable detergent cleaning.
- Remove salts, detergents and other contaminants by high pressure fresh water cleaning.

### New build:

- Abrasive blasting to min. Sa 2½ (ISO 8501-1) / SP 10 (SSPC).
- Remove dust, blast media and loose materials.

### Maintenance and Repair

- Spot abrasive blasting to min. PSa 2½ (ISO 8501-2) / SP 10 (SSPC).
- Minor areas can be cleaned by power tool to St 3 provided the surface is roughened and not polished.
- Remove dust, blast media and loose materials.

# Hempadur Multi-Strength 45703

## Roughness

- Surface profile Medium (G) (ISO 8503-2).

Consult Hempel's separate Surface Preparation Guidelines for more details.

## Application

### Mixing ratio

Base 45705 : Curing agent 98750  
(3 : 1 by volume)

Stir well before use.

### Thinner

Hempel's Thinner 08450

### Cleaner

Hempel's Tool Cleaner 99610

### Pot life

<b>Product temperature</b>	<b>20°C</b> [68°F]
Pot life	60 min

### Application method

Tool	Application parameters
Airless spray	Nozzle pressure: 250 bar [3600 psi] Nozzle orifice: 0.021-0.023"

Spray data are indicative and subject to adjustment. Pressure is for a material temperature of 20°C [68°F].

## Film thickness

Specification range	Low	High	Recommended
Dry film thickness	150 micron [5.9 mils]	300 micron [12 mils]	200 micron [7.9 mils]
Wet film thickness	210 micron [8 mils]	450 micron [16 mils]	290 micron [11 mils]
Theoretical spreading rate	4.7 m <sup>2</sup> /L [190 sq ft/US gal]	2.3 m <sup>2</sup> /L [94 sq ft/US gal]	3.5 m <sup>2</sup> /L [140 sq ft/US gal]

Product may be specified in another film thickness than indicated depending on purpose and area of use. This will alter spreading rate, drying and curing time and overcoating interval. For best performance, avoid excessive film thickness.

## Application conditions

- Surface temperature must be above -10°C [14°F] during application and curing.
- Temperature of product must be above 15°C [59°F] during application.
- To avoid condensation, apply on a clean and dry surface with a temperature that is at least 3°C [5°F] above the dew point.

## Relative Humidity:

- Relative humidity must be below 90% during curing.
- Relative humidity must be below 90% during application.

## Application remarks

- Product requires heavy duty spray equipment; spray hoses shall be as short as possible.

## Drying and overcoating

### Product compatibility

- Previous coat: None or according to Hempel's specification.
- Subsequent coat: None or according to Hempel's specification.  
Recommended products are: Hempadur Multi-Strength

### Drying time

Surface temperature		10°C	20°C
		[50°F]	[68°F]
Hard dry	hours	10	5½

Determined for dry film thickness 200 micron [7.9 mils] at standard conditions, see Hempel's Explanatory Notes for details.

# Hempadur Multi-Strength 45703

## Overcoating

Hempel's specification supersedes any guidelines indicated in the overcoating table

Quality name	-10°C [14°F]		0°C [32°F]		20°C [68°F]	
Atmospheric medium						
Hempadur Multi-Strength 45703	Min	36 h	18 h	4 h		
	Max	90 d	90 d	30 d		
Immersion						
Hempadur Multi-Strength 45703	Min	45 h	23 h	5 h		
	Max	90 d	90 d	30 d		

Overcoating times are indicative for products of the same generic chemistry. Consult Hempel's specification for more information.

## Drying conditions

- To obtain the drying time stated, it is important to maintain sufficient ventilation during application, drying and curing.

## Overcoating details

- If the maximum overcoating interval is exceeded, roughening of the surface is necessary to ensure intercoat adhesion.
- The surface must be dry and clean prior to application.

## Other remarks

- Epoxy coats have an inherent tendency of chalking in outdoor exposure. This does not affect the performance of the coating.
- Hempel's Specification supersedes any recommendations given in the Product Data Sheets.

## Storage

### Shelf life

Ambient temperature	25°C [77°F]	35°C [95°F]
Base	36 months	24 months
Curing agent	36 months	24 months

Shelf life from date of production, when stored in original, unopened containers. Thereafter, the product quality must be re-inspected. Always check the best before date or expiry date on the label.

## Additional documents

Additional information is available at the Hempel website [hempel.com](http://hempel.com) or at your local Hempel website:

- Explanatory Notes explaining the fields in this Product Data Sheet.
- Surface Preparation Guidelines.
- Application Guidelines for different application methods.
- General Application Guidelines

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. Accordingly, the buyer/applicator should have regard to the PDS supplied together with the relevant batch of the Product (and not an earlier version). In addition to the PDS, the buyer/applicator may receive some or all of the following specifications, statements and/or guidelines as listed below or as are available from the Hempel website under 'Products' at [www.hempel.com](http://www.hempel.com) (the "Additional documents"):

No.	Document description	Location/comments
1.	Technical Statement	One-off specific advice provided on request for specific projects
2.	Specification	Only issued for specific projects
3.	PDS	This document
4.	Explanatory Notes to the PDS	Available at <a href="http://www.hempel.com">www.hempel.com</a> and contain relevant information about the Product testing parameters
5.	Application Instruction	Where available, at <a href="http://www.hempel.com">www.hempel.com</a>
6.	Generic technical guidelines (e.g. on application and surface preparation)	Where available, at <a href="http://www.hempel.com">www.hempel.com</a>

In the event of a conflict of information between the PDS and the Additional documents, the order of priority of information shall be in the order as set out above. In such event you should also contact your representative at Hempel for clarification. Furthermore, the buyer/applicator must have full regard to the relevant Safety Data Sheet provided with each Product and which can also be downloaded from [www.hempel.com](http://www.hempel.com).

Hempel shall not be liable for defects where the application of the Product has not been made fully in accordance with the recommendations and requirements set out in the relevant PDS and the Additional Documents. The information and terms of this disclaimer apply to this PDS, the Additional documents and any other documents supplied by Hempel in respect of the Product. In addition, the Product is supplied and all technical assistance is given subject to Hempel's General Conditions of Sale, Delivery and Service, unless otherwise expressly agreed in writing.