

Hempasil Nexus X-Tend 27500

Product characteristics

Description

Hempasil Nexus X-tend 27500 is a high solids tie-coat used for repairs and touch-ups in Hempaguard®/Hempasil systems.

Recommended use

Hempasil Nexus X-tend 27500 is a tie-coat for the Hempaguard®/Hempasil topcoats used for touch-up and repair of damaged areas of existing silicone topcoats securing the adhesion between the anticorrosive system and the Hempaguard®/Hempasil topcoat. Minimum curing temperature: 5°C [40°F]. Also recommended as a low temperature tie-coat used in combination with Hempel's Nexus II 27400 for full coat applications of the Hempaguard®/Hempasil topcoats. Minimum curing temperature for this system is 0°C [32°F].

Product safety

Flash point 28°C [82°F]

VOC content

Legislation	Value
EU	259 g/L [2.16 lb/US gal]
US (coatings)	249 g/L [2.08 lb/US gal]
US (regulatory)	249 g/L [2.08 lb/US gal]
China	259 g/L [2.16 lb/US gal]

According to specific legislation, see details in the Explanatory Notes available at Hempel website, hempel.com or at your local Hempel website.

Handling

Handle with care. Before and during use, observe safety labels on packaging and paint containers and follow all local and national safety regulations. Always consult Hempel's Safety Data Sheet for this product along with the Product Data Sheet.

For professional use only.

Product data

Product code

27500

Standard shade / code

Cream 23410

Gloss

Semi-gloss

Volume solids

65 ± 2%

Specific gravity

1.2 kg/L [10 lb/US gal]

Reference dry film thickness

120 micron [4.7 mils]

Surface preparation

New build:

- According to Hempel's Specification.

Maintenance and Repair

- According to Hempel's Specification.

Consult Hempel's separate Surface Preparation Guidelines for more details.

Application

Mixing ratio

Stir well before use. Thinning is not allowed. This product contains heavy particles. Stir well before use.

Thinner

No thinning

Cleaner

Hempel's Thinner 08080

Hempasil Nexus X-Tend 27500

Application method

Tool	Thinning max vol.	Application parameters
Airless spray	No thinning	Nozzle pressure: 150 bar [2200 psi] Nozzle orifice: 0.019-0.021"
Brush	No thinning	Not Applicable.

If brush or roller application is used, more coats will be necessary to achieve the specified dry film thickness. Spray data are indicative and subject to adjustment. Pressure is for a material temperature of 20°C [68°F].

Film thickness

Specification range	Low	High	Recommended
Dry film thickness	100 micron [3.9 mils]	120 micron [4.7 mils]	120 micron [4.7 mils]
Wet film thickness	150 micron [6 mils]	190 micron [7 mils]	190 micron [7 mils]
Theoretical spreading rate	6.5 m ² /L [260 sq ft/US gal]	5.5 m ² /L [220 sq ft/US gal]	5.5 m ² /L [220 sq ft/US gal]

It is vital that the specified minimum dry film thickness is uniformly achieved. For best performance, avoid excessive film thickness.

Application conditions

- To avoid condensation, apply on a clean and dry surface with a temperature that is at least 3°C [5°F] above the dew point.
- Temperature of product must be above 15°C [59°F] during application.
- Optimal paint temperature for proper mixing, pumping and spraying is: 20°C [68°F].

Relative Humidity:

- Relative humidity must be in the range 30-85% during curing.
- Relative humidity must be in the range 30-85% during application.

Drying and overcoating

Product compatibility

- Previous coat: According to Hempel's Specification. Recommended products are: Hempadur 15570, Hempel's Nexus II 27400
- Subsequent coat: According to Hempel's Specification. Recommended products are: Hempasil, Hempaguard®.

Drying time

Surface temperature		10°C [50°F]	20°C [68°F]	30°C [86°F]
Hard dry	hours	4½	2¼	1½
Fully cured	days	4	2	1½

Determined for dry film thickness 120 micron [4.7 mils] at standard conditions, see Hempel's Explanatory Notes for details.

Overcoating

Consult Hempel's specification for more information.

Drying conditions

- To obtain the drying time stated, it is important to maintain sufficient ventilation during application, drying and curing.
- Condensation on the freshly applied coating should be avoided.

Storage

Shelf life

Ambient temperature	25°C [77°F]	35°C [95°F]
Product	18 months	18 months

Shelf life from date of production, when stored in original, unopened containers. Thereafter, the product quality must be re-inspected. Always check the best before date or expiry date on the label.

Storage conditions

- Product must be stored according to local legislation, at maximum 40°C [104°F], without direct sunlight and protected from rain and snow.

Hempasil Nexus X- Tend 27500

Additional documents

Additional information is available at the Hempel website hempel.com or at your local Hempel website:

- Explanatory Notes explaining the fields in this Product Data Sheet.
- Surface Preparation Guidelines.
- Application Guidelines for different application methods.
- Consult Hempel's separate guideline on general requirements for Hempaguard/Hempasil application.

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. Accordingly, the buyer/applicator should have regard to the PDS supplied together with the relevant batch of the Product (and not an earlier version). In addition to the PDS, the buyer/applicator may receive some or all of the following specifications, statements and/or guidelines as listed below or as are available from the Hempel website under 'Products' at www.hempel.com (the "Additional documents"):

No.	Document description	Location/comments
1.	Technical Statement	One-off specific advice provided on request for specific projects
2.	Specification	Only issued for specific projects
3.	PDS	This document
4.	Explanatory Notes to the PDS	Available at www.hempel.com and contain relevant information about the Product testing parameters
5.	Application Instruction	Where available, at www.hempel.com
6.	Generic technical guidelines (e.g. on application and surface preparation)	Where available, at www.hempel.com

In the event of a conflict of information between the PDS and the Additional documents, the order of priority of information shall be in the order as set out above. In such event you should also contact your representative at Hempel for clarification. Furthermore, the buyer/applicator must have full regard to the relevant Safety Data Sheet provided with each Product and which can also be downloaded from www.hempel.com.

Hempel shall not be liable for defects where the application of the Product has not been made fully in accordance with the recommendations and requirements set out in the relevant PDS and the Additional Documents. The information and terms of this disclaimer apply to this PDS, the Additional documents and any other documents supplied by Hempel in respect of the Product. In addition, the Product is supplied and all technical assistance is given subject to Hempel's General Conditions of Sale, Delivery and Service, unless otherwise expressly agreed in writing.